

TECHNICAL DATA SHEET
HVCRC® 370 - 47
 Epsilon Advanced Conductors

EPSILON
CABLE

International size	AMSTERDAM
ASTM Size	DOVE
Technical designation	ECRC® 370-AL0/47-S1



Governing Units: Metric

STRANDING CONFIGURATION

	No. & Diameter of HVCRC core	1 x 7.75	mm
	Aluminium Layers Construction / height	18 TW x	3.95 mm
	1st layer composition and ϕ_{eq}	7 x	5.03 mm
	2nd layer composition and ϕ_{eq}	11 x	5.16 mm
	Lay Direction of outer layer	Right Hand (Z)	

CONDUCTOR PROPERTIES


Cross Sectional Area - Annealed Aluminium	369.0	mm ²
Cross Sectional Area - HVCRC Core	47.2	mm ²
Total Area of Conductor Cross Section	416.1	mm ²
Nominal equivalent Aluminium Area (1350-H19 at 61%IACS)	381.0	mm ²
Overall Diameter of Conductor	23.55	mm
Mass per unit length - Annealed Aluminium	1,020.0	kg/km
Mass per unit length - Core	87.3	kg/km
Mass per unit length - Conductor	1,107.3	kg/km
Ultimate Tensile Strength of Conductor	128.0	kN
Core Rated Tensile Strength	105.8	kN
Coefficient of Linear Expansion Above Thermal Kneepoint	1.3	10 ⁻⁶ K ⁻¹
Coefficient of Linear Expansion Below Thermal Kneepoint	18.17	10 ⁻⁶ K ⁻¹
Final Modulus of Elasticity Above Thermal Kneepoint	123	GPa
Final Modulus of Elasticity Below Thermal Kneepoint	63	GPa

THERMAL SPECIFICATIONS

Maximum Continuous Operating Temperature ⁽²⁾ (surface temperature)	180	°C
Maximum Emergency Temperature / 8760 Hours ⁽²⁾ (surface temperature)	200	°C
Thermal Heat Capacity for Annealed Aluminium Layers	974.1	W.s/m.°C
Thermal Heat Capacity for Composite Core	69.8	W.s/m.°C

ELECTRICAL SPECIFICATIONS

Maximum DC Electrical Resistance at 20°C (1370-O at 63%IACS)	0.0759	Ω.km ⁻¹
Temperature Coefficient of Resistance	4.03	10 ⁻³ K ⁻¹
AC Nominal Resistance at 25°C (surface temperature)	0.0785	Ω.km ⁻¹
AC Nominal Resistance at 75°C (surface temperature)	0.0936	Ω.km ⁻¹
AC Nominal Resistance at 160°C (surface temperature)	0.1194	Ω.km ⁻¹
AC Nominal Resistance at 180°C (surface temperature)	0.1255	Ω.km ⁻¹
AC Nominal Resistance at 200°C (surface temperature)	0.1316	Ω.km ⁻¹
AC Current Rating at 160°C (surface temperature) ⁽¹⁾	1,374	A
AC Current Rating at 180°C (surface temperature) ⁽¹⁾	1,461	A
AC Current Rating at 200°C (surface temperature) ⁽¹⁾	1,543	A


Geometric Mean Radius (GMR)

9.57 mm

Inductive Reactance Ø0.3m radius

 0.217 Ω.km⁻¹
Capacitive Reactance Ø0.3m radius

0.186 MΩ.km

(1) Ampacity calculations based on IEEE Standard 738-2012, according to the following data:

25 °C ambient temperature, 0.61 m/s wind velocity with an angle of 90 °,
 1000 W/m² solar radiation, 0.5 solar absorption coefficient,
 0.6 emissivity coefficient, Resistance AC at 50 Hz current frequency.

(2) Temperatures defined according to ASTM B987-20.

Reference standards for core properties: ASTM B987-20.

Reference standards for electrical specifications: IEC 62219.

Reference standards for stranding parameters: ASTM B857-14/IEC 62219.

Depending on conductor manufacturer rated specifications may slightly change.

Revision 02
 Ref. Document ST21-00089
 Date 12-Sep-2023

This document is the property of EPSILON COMPOSITE
contact@epsilon-cable.com
www.epsilon-cable.com